

# Catena calibrata OSC

## OSC calibrated chain



### Marchatura per identificazione

segno di fiducia nel  
prodotto e strumento di  
rintracciabilità

### Branded chain

Reliability and confidence



# Catena calibrata OSC

## OSC calibrated chain



Confezionamento in cassa di legno  
con indicazione di codice, diametro e lunghezza

Wooden case clearly showing chain specs  
(PN, diameter and length)



# Test nebbia salina

## Salt spray chamber test



Controllo effettuato  
a campione su ogni  
lotto

Quality check  
for each batch



**Test effettuato il 05/04/2017**

**Test made in 05/04/2017**



**Condizioni a fine test**

**Chain after the test**



# Condizioni a fine test

## Chain after the test



# Metodo standard ASTM 117

## Standard method ASTM 117

Durata test 114 h assimilabili a 2anni di uso in ambiente salino  
Test duration 114 h same as 2 years of marine use



**ESITI TEST del 05/04/17:**

**RESULTS FOR TEST made 05/04/17:**

**01.373.10** galvanised chain: nessun segno o presenza di ruggine  
no rust presence sign

**01.375.10** stainless steel chain: nessun segno o presenza di ruggine  
no rust presence sign

Mauro Di Giorgio  
Customer Technical Support

A handwritten signature in black ink, appearing to read "Mauro Di Giorgio", is positioned below the printed name and title.

# Test resistenza su ogni lotto

## Load test on each batch



PART NUMBER	WORKING LOAD	BREAKING LOAD
01.373.06-XXX	400 KGS	16.0 KN
01.373.08-XXX	800 KG	32.0 KN
01.373.10-XXX	1,250 KGS	50.0 KN
01.373.12-XXX	1,810 KGS	72.4 KN
01.373.14-XXX	2, 300 KGS	92.4 KN
01.375.06-XXX	450 KGS	18.0 KN
01.375.08-XXX	800 KGS	32.0 KN
01.375.10-XXX	1, 250 KGS	50.0 KN
01.375.12-XXX	1, 810 KGS	72.4 KN
01.375.14-XXX	2, 300 KGS	92.4 KN

**Carichi di rottura e lavoro**  
Breaking and working loads test

Mauro Di Giorgio  
Customer Technical Support